

No. 1007-E

October 7th, 2014
Typical Properties of LHL-X100

Test item	Test	Property
Appearance	--	Semi-fluid
Color	--	Yellow
Worked penetration	JIS K2220 7.	460
Drip point	JIS K2220 8.	180
Copper Corrosion (100°C, 24h)	JIS K2220 9.B	Pass *
Evaporation loss (99°C, 22h) w.t.%	JIS K2220 10.	0.31
Oil Separation (100°C, 24h) w.t.%	JIS K2220 11.	N/A
Oxidation Stability (99°C, 100h) kPa	JIS K2220 12.	5
Load carrying capacity	LNL	1236
High speed 4 ball test	WL	1569
	N LWI	480
Thickener	--	Urea
Base oil viscosity mm ² /s	(40°C)	JIS K2220 23.
		114

* No change in color into green or black on copper plate is observed.

LUBE CORPORATION